


In the Claims


1. (canceled)

2. (previously presented) A mixture comprising

i) a compound of the formula I



wherein




R_2 is $\text{C}_7\text{-C}_{30}$ alkyl,

R_3 is $\text{C}_1\text{-C}_{30}$ alkyl,

and

ii) an antistatic agent selected from the group consisting of an ethoxylated amide and a compound of the formula V



wherein, ~~when m is 1,~~

~~R₆ is C₄-C₂₄alkyl, C₄-C₂₄alkenyl or phenyl, and~~

~~when m is 2,~~

~~R₆ is C₄-C₂₄alkylene, C₄-C₂₄alkenylene or phenylene,~~

~~R₇ is hydrogen, C₄-C₂₄alkyl or $\left[\text{CH}_2\text{CH}_2\text{O} \right]_n \text{H}$,~~

~~R₈ $\left[\text{CH}_2\text{CH}_2\text{O} \right]_n \text{H}$,~~

~~m is 1 or 2, and~~

~~n is 1, 2, 3, 4 or 5~~

R₆ is C₁₁-C₂₀alkyl or C₁₁-C₂₀alkanoyl,

R₇ is hydrogen or $\left[\text{CH}_2\text{CH}_2\text{O} \right]_n \text{H}$

R₈ is $\left[\text{CH}_2\text{CH}_2\text{O} \right]_n \text{H}$

m is 1, and

n is 1.


3. (previously presented) A mixture according to claim 2, comprising in addition, besides components (i) and (ii), further additives selected from the group consisting of phenolic antioxidants, further processing stabilizers, light-stabilizers and acid scavengers.

4. (previously presented) A mixture according to claim 2, comprising as a further component (iii) a phosphite, a phosphonite or a triarylphosphine.

5. (original) A mixture according to claim 4, wherein component (iii) is tris(2,4-di-tert-butylphenyl)phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite, bis(2,4-dicumylphenyl)pentaerythritol diphosphite, tris(nonylphenyl) phosphite or tetrakis(2,4-di-tert-butylphenyl)4,4'-biphenylene diphosphonite.


6-9. (canceled)

10. (original) A mixture according to claim 2, comprising as component (i) a compound of the formula I, wherein



11-13. (canceled)

14. (previously presented) A mixture according to claim 2, wherein component (i) is a compound of the formula I



C₁₃-C₁₈-alkyl-diethanolamine.

15. (previously presented) A composition comprising

- a) an organic material which is susceptible to oxidative, thermal or light-induced degradation, and
- b) a mixture of components (i) and (ii) according to claim 2.

16. (original) A composition according to claim 15, wherein component (a) is a synthetic polymer.

17. (original) A composition according to claim 15, wherein component (a) is a polyolefin.

18. (original) A composition according to claim 15, wherein component (a) is polyethylene or polypropylene or mixture thereof.

19. (original) A composition according to claim 15, wherein component (b) is present in an amount of from 0.001 to 5 %, based on the weight of component (a).

20. (previously presented) A shaped article containing a mixture according to claim 2.

21. (previously presented) A process for stabilizing an organic material against oxidative, thermal or light-induced degradation, which comprises incorporating therein or applying thereto at least a mixture according to claim 2.

22. (canceled)